

Solar protection

SOLTIS® 92

Technical properties	Soltis® 92	Standards
Weight	420 g/m ²	EN ISO 2286-2
Thickness	0,45 mm	
Roll width	177 cm	
Tensile strength (warp/weft)	310/210 daN / 5 cm	EN ISO 1421
Tear resistance (warp/weft)	40/20 daN	DIN 53.363
Flame retardancy	M1/NFP 92-507 • Test 1/NFPA 701 • CSFM T19 • ASTM E84 • B1/DIN 4102-1 • BS 7837 • B1/ONORM B 3800-1 • CLASSE 1/UNI 9177 • M1/UNE 23.727 • VKF 5.3/SN 198898 B-s2,d0/EN 13501-1	
Euroclass		
Roll lengths	50 lm	
Quality management system		ISO 9001
Environmental management system		ISO 14001

The technical data shown here are average values, given for information only, and may be modified.



● Austronet ▲ Austral ■ Austral Nano ● Printable FR Flame retardant treatment available